


# PLATINA LUXOL HI-GLOSS ENAMEL



## Colour Range



- Golden Yellow • Smoke Grey
- Phiroza Blue • Deep Orange
- Black • White



**Fire Hazard Class**  
Flammable



**Pot Life of Thinned Material**  
Within 24hrs

## Shelf Life

3 -4 years from the date  
of manufacture

## Product Description

LuxolHigh Gloss Enamel offers a mirror – like gloss to mild steel, wooden and suitable prepared masonry surfaces due to its chemical composition of alkyd and select colourants. The paint can be used for both interior and exterior surfaces.

## Recommended Use

Mild steel, wood, and prepared masonry surfaces.

## Recommended Primers

- Wall/Plastered surfaces – BP Cement Primer (ST)
- Metal surfaces - Butterfly A/C Metal Primer, Luxol Zinc Chromate Primer
- Wooden surfaces – Parrot Wood Primer

## Coverage



Brush application - approx.  
90-120sq.ft/L/2 coats, under ideal test  
conditions

(Coverage may depend on factors like surface conditions, surface  
preparation, application skill, weather conditions, dilution etc.)

## Drying Time



**SD:** 3 -4hrs

**HD:** Overnight depending on  
weather conditions

## Recommended Dilution



10 - 15% (v/v)

## Application Method



Brush, Felt Roller & Spray

## Recommended Thinner



Thinner 800

## Flash Point



Not below 37° C

## Gloss Level



80 ± 5 at 60° GH on tin plate  
when released

## Viscosity



Brushing – 40 - 45 sec at 30°C  
Spraying – 20 - 30 sec at 30°C  
Roller – 60 - 65 sec at 30°C

# PLATINA LUXOL HI-GLOSS ENAMEL



## Packs



20 L

### Surface Preparation

**For Cement plaster/ Wood /Metal surface:**




Initially sand the surface with coarse Sandpaper / Water paper according to the type of surface to be prepared. Remove rust, dust and other loose unwanted particles.

Wipe the surface clean.

### Application Process

**Primer Application:**

one coat of primer after proper dilution and allow it to dry fully.



Sand the surface again with less coarser Water paper and wipe clean. Again apply 2 coats of primer giving overnight interval between coats.

Sand it again with Water paper No.220/280.

**For Wooden & Metal surface:** Apply one coat of Luxol Speed Coat Primer Surfacer with proper dilution.

**For Wall surface:** Apply one coat of solvent-based Cement Primer with ideal dilution.

Allow the surfaces to dry dully. Then sand the primed surface with Water Paper No. 380/400 lightly to make the surface smooth and undulation free.

### Application of Topcoat:



Before the application of topcoat, dilute the paint as mentioned above and strain it through a clean cloth.

Ensure Surface pH value is within 7-11.

Ensure the painting brush and mixing container are absolutely clean.

Use felt roller to get an orange peel effect.



Apply 3 coats of LuxolHigh Gloss Enamel to get rich, smooth and high-gloss finish.

Give overnight drying interval between coats.

Luxol High- gloss enamel should not be used on damp surfaces subjected continuous seepage.

### Points to Note

- ▶ Shake well before use and do not over dilute
- ▶ Strain the material through a fine sieve before use
- ▶ Keep the container tightly closed to prevent drying
- ▶ Use 1 -2 coats of Bio - Wash for killing fungal growth
- ▶ Keep out of reach of children and away from foodstuff
- ▶ In case of contact with eyes, wash immediately with water and seek medical help
- ▶ For deeper shade apply 1 additional coat

### Special Note

Use only toilet soap to clean stains

Before painting the following things should be checked thoroughly:

1. Moisture content of the wall (ideal condition - below 12%)
2. pH value of the wall surface (ideal condition - between 7-11)

Version No: BPP1/12/2019. Please note that this data sheet supersedes all previous versions.

## BERGER PAINTS INDIA LIMITED

Berger House, 129 Park Street, Kolkata 700 017 | CONSUMER RELATIONS MANAGER Ph: 1800-103-6030  
Fax: 91-33-2249-9729/9009 | SMS BERGER to 56767 | Email: consumerfeedback@bergerindia.com | www.bergerpaints.com