



WeatherCoat Long Life XP Advanced

Product Description : WeatherCoat Long Life XP Advanced is a premium exterior emulsion paint with high sheen. The paint is formulated with a special grade of inorganic and organic hybrid acrylic polymer, fortified with polyurethane emulsion which gives high level of mechanical properties. Special grades of light fast pigments and additives enhance the paint's durability. Due to the use of unique technology in the composition, the paint demonstrates high performing properties such as long-term protection of the surface and extended new look. It also resists chalking, flaking, fading and prevents the growth of fungus and algae over a period of time.

USP : High performance paint, Provides long-term protection to the surface with an extended new look. Resistant to chalking, flaking, fading and prevents the growth of fungus and algae.

Usage Area : WeatherCoat Long Life XP Advanced is suitable for sand/cement plaster surfaces, concrete and asbestos.

Note : This product is not recommended on lime wash.

DIRECTIONS FOR USE

Surface Preparation : For new masonry, the surface should be allowed to cure properly. Apply one coat of Illusion Sealer to avoid the problem of salt petering.

Previously Painted Surfaces : For old surface, ensure the surface is free from loose paints, dust, grease, fungus and algae by sanding or wire brushing. Cracks, holes, dents and damp areas should be repaired properly before painting.

Treat the surface with Bio-wash solution and wash it next day with potable water and then let the surface dry completely.

Priming : Apply 1 – 2 coats of WC Seal-O-Primer XP. For best performance, apply WC Elastomeric Primer.

Direction for Application : Apply 2-3 coats of topcoat keeping an interval of 4-6 hours between each coat.

COVERAGE

All in 1 coat primed surface	Brush Application
No. of coats	2 coats
New surface	60 – 70 sq. ft. / Lt

- It depends on many factors like surface conditions, surface preparation, application skill, weather conditions, dilution etc. The coverage mentioned is under ideal conditions and will vary depending on site conditions.

TECHNICAL DATA

1	Recommended Thinner		6	Pot Life of Thinned Material	Within 24 hrs
2	Dilution Ratio	40% by volume. For dark shades : 0 – 10 %	7	Flash Point	Non-combustible
3	Application Tools	Brush, Roller and Conventional Spray	8	Unusual Fire & Explosion Hazards	Material can splatter above 212 F. Polymer film can burn.
4	Drying Time	Surface Dry : 30 min Hard Dry : 4 – 6 hrs	9	Over-coating interval	4 – 6 hrs
5	Gloss at 60°	GH: 12 – 16			

PRECAUTIONS

Stir and strain the diluted paint well before use.

Do not over dilute or over extend brush.

Do not apply paint on high alkaline surface.

Do not apply paint on a wet surface.

Do not apply paint on chalking or flaking surface or where the surface is infected with fungus and algae.

Do not apply paint if the ambient temperature is less than or expected to fall below 10 C

HEALTH & SAFETY

Move the person to fresh air.

If the paint comes in contact with eyes and skin, then flush with a large amount of water for at least 15 minutes. See a physician, if irritation persists. Wash affected skin areas with soap and water.

Version No: BPP1/11/2014. Please note that this data sheet supersedes all previous versions.

BERGER PAINTS INDIA LIMITED

Berger House, 129 Park Street, Kolkata 700 017 | CONSUMER RELATIONS MANAGER Ph: 1800-103-6030
Fax: 91-33-2249-9729/9009 | SMS BERGER to 56767 | Email: consumerfeedback@bergerindia.com | www.bergerpaints.com